



CERTIFICATE of PERFORMANCE SEFA-8 SPECIFICATION

Kewaunee Scientific Corporation certifies that its laboratory furniture identified as Steel Base Unit (E40M3748), Steel Wall Case (SW-1258-00), and Steel Table (SA-6022/SA-2229) have been tested in conformance with the full requirements of the SEFA-8 Specification with results noted below.

TEST	TEST RESULTS PASS/FAIL	TEST	TEST RESULTS PASS/FAIL	TEST	TEST RESULTS PASS/FAIL
4.2	Pass	6.1	Pass	8.1	See Attached Form
4.3	Pass	6.2	Pass	8.2	Pass
4.4	Pass	6.3	Pass	8.3	Pass
4.5	Pass	6.4	Pass	8.4	Pass
5.1	@ 200 lbs. - Pass	6.5	@ 100 lbs.	8.5	Pass
5.2	Pass	6.5	@ 150 lbs. - Pass	9.2	Pass
5.3	Pass	7.1	Deflection Measured: .08 inches	10.2	Pass

Full documentation of the test results is available upon request in a bound report that includes a detailed description of the test unit and procedures, witnessed results, and appropriate drawings or photographs of the test unit and procedures.

COMPANY INFORMATION	TEST SUPERVISOR INFORMATION
Name: Kewaunee Scientific Corporation	Name: David Foote
Address: 2700 West Front Street Statesville, NC 28677	Title: Manager of Research & Development
	Signature: 
Telephone: (704) 873-7202	COMPANY OFFICER INFORMATION
Fax: (704) 873-1275	Name: Kurt P. Rindoks
	Title: V. P., Engineering & Product Development
Date: November 1997	Signature: 

CHEMICAL RESISTANCE TESTING - 8.1

Date of Test:
July 8, 1997

Sample Description:
Removable Back

Type Material Coated:
Metal

Coating Type:
Top Coat # 20

SCALE: Level 0.....No Detectable Change
 Level 1.....Slight Change in Color or Gloss
 Level 2.....Slight Surface Etching or Severe Staining
 Level 3.....Pitting, Cratering, Swelling, Erosion of Coating. Obvious & Significant Deterioration.

#	CHEMICAL	RATING	COMMENTS
1	Amyl Acetate	0	
2	Ethyl Acetate	1	
3	Acetic Acid 98%	1	
4	Acetone	1	
5	Acid Dichromate 5%	0	
6	Butyl Alcohol	0	
7	Ethyl Alcohol	0	
8	Methyl Alcohol	0	
9	Ammonium Hydroxide 28%	0	
10	Benzene	1	
11	Carbon Tetrachloride	0	
12	Chloroform	1	
13	Chromic Acid 60%	0	
14	Cresol	0	
15	Dichlor Acetic Acid	2	Slight bubbling of paint
16	Dimethylformamide	0	
17	Dioxane	0	
18	Ethyl Ether	1	
19	Formaldehyde 37%	0	
20	Formic Acid 90%	0	
21	Furfural	1	
22	Gasoline	0	
23	Hydrochloric Acid 37%	0	
24	Hydrofluoric Acid 48%	1	
25	Hydrogen Peroxide 28%	0	
26	Tincture of Iodine	0	

SCALE: Level 0..... No Detectable Change
 Level 1.....Slight Change in Color or Gloss
 Level 2.....Slight Surface Etching or Severe Staining
 Level 3.....Pitting, Cratering, Swelling, Erosion of Coating, Obvious & Significant Deterioration

#	CHEMICAL	RATING	COMMENTS
27	Methyl Ethyl Ketone	1	
28	Methylene Chloride	1	
29	Mono Chlorobenzene	1	
30	Naphthalene	0	
31	Nitric Acid 20%	0	
32	Nitric Acid 30%	0	
33	Nitric Acid 70%	0	
34	Phenol 90%	1	
35	Phosphoric Acid 85%	0	
36	Silver Nitrate, Saturated	0	
37	Sodium Hydroxide 10%	0	
38	Sodium Hydroxide 20%	0	
39	Sodium Hydroxide 40%	0	
40	Sodium Hydroxide, Flake	0	
41	Sodium Sulfide, Saturated	0	
42	Sulfuric Acid 25%	0	
43	Sulfuric Acid 85%	1	
44	Sulfuric Acid 96%	3	Took off portion of topcoat, not e-coat
45	Sulfuric Acid 85%, and Nitric Acid 70%, equal parts	1	
46	Toluene	1	
47	Trichloroethylene	1	
48	Xylene	0	
49	Zinc Chloride, Saturated	0	

TEST PERFORMED BY: James Rufty

DATE: July 8, 1997